



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
11.09.2002 Bulletin 2002/37

(51) Int Cl.7: **B01J 13/02, B01J 33/00,
B01J 31/16, B01J 23/46,
C07C 29/48**

(21) Application number: **99103375.4**

(22) Date of filing: **22.02.1999**

(54) **Microencapsulated osmium oxide composition**

Mikroverkapselte Osmiumoxidzusammensetzung

Composition d'oxide d'osmium micro-encapsulée

(84) Designated Contracting States:
AT BE CH DE DK ES FR GB IT LI NL SE

(30) Priority: **02.03.1998 JP 6620798**

(43) Date of publication of application:
08.09.1999 Bulletin 1999/36

(73) Proprietors:
• **Wako Pure Chemical Industries, Ltd.**
Osaka 541-0045 (JP)
• **Kobayashi, Shu**
Tokyo 101-0064 (JP)

(72) Inventor: **Kobayashi, Shu**
Tokyo 101-0064 (JP)

(74) Representative:
von Kreisler, Alek, Dipl.-Chem. et al
Patentanwälte,
von Kreisler-Selting-Werner,
Bahnhofsvorplatz 1 (Deichmannhaus)
50667 Köln (DE)

(56) References cited:
WO-A-91/00143 DE-A- 2 835 943
US-A- 5 260 461

• **CAINELLI ET AL.: "Catalytic Hydroxylation of
Olefins by Polymer-Bound osmium Tetroxide"**
SYNTHESIS, no. 1, 1989, pages 45-47,
XP002136423

• **PATENT ABSTRACTS OF JAPAN vol. 015, no.**
252 (C-0844), 26 June 1991 (1991-06-26) & JP 03
081337 A (MATSUSHITA ELECTRIC IND CO
LTD), 5 April 1991 (1991-04-05)

• **CHOONG E S ET AL: "Polymeric Cinchona**
Alkaloids for the Heterogeneous Catalytic
Asymmetric Dihydroxylation of Olefins: The
Influence of the Polymer Backbone Polarity on
the Compatibility between Polymer Support and
Reaction Medium" TETRAHEDRON:
ASYMMETRY,NL,ELSEVIER SCIENCE
PUBLISHERS, AMSTERDAM, vol. 6, no. 11, 1
November 1995 (1995-11-01), pages 2687-2694,
XP004047975 ISSN: 0957-4166

• **PINI, DARIO ET AL.: "Heterogeneous catalytic**
asymmetric dihydroxylation of olefins: a new
polymeric support and a process improvement"
TETRAHEDRON, vol. 50, no. 38, 1994, pages
11321-11328, XP002136424

• **KOLB H C ET AL: "CATALYTIC ASYMMETRIC**
DIHYDROXYLATION" CHEMICAL
REVIEWS,US,AMERICAN CHEMICAL SOCIETY.
EASTON, vol. 94, 1994, pages 2483-2547,
XP000857717 ISSN: 0009-2665

• **NAGAYAMA, S ET AL.: "Microencapsulated**
Osmium Tetraoxide. A New Recoverable and
Reusable Polymer -Supported Osmium Catalyst
for Dihydroxylation of Olefins" J. ORG. CHEM.,
[Online] vol. 63, 13 August 1998 (1998-08-13),
pages 6094-6095, XP002136425 Retrieved from
the Internet:
<URL:http://pubs.acs.org/CHECKCCIP-95675
13 04/isubscribe/journals/joceah/63/i18/pdf/j
o981127y.pdf> [retrieved on 2000-04-25]

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

BACKGROUND OF THE INVENTION

[0001] The present invention relates to osmium oxide microencapsulated in an aromatic polyolefin and osmium oxide-chiral ligand complex microencapsulated in an aromatic polyolefin, which makes it possible to conduct an oxidation reaction of organic compounds in an enlarged industrial production scale.

[0002] It has been said that, among osmium oxide compounds, only oxides of tetravalent and octavalent osmium are actually existing in separated form, but additionally, oxides of divalent, trivalent and hexavalent osmium may be considered to exist.

[0003] The oxides of octavalent osmium have been called osmium tetroxide or osmic acid when it is in an aqueous solution, and the oxides show a strong oxidation ability and thus they have been used as a special oxidizing agent and a catalyst in an organic synthesis. However, osmium tetroxide shows a melting point of 40.6 to 40.7°C, a boiling point of 131.2°C and vapor pressure of 9.3 hPa/20°C (7mm /20°C) and 69.3 hPa/55°C (52mm/55°C), and has a peculiar smell which can be perceived even in such an extraordinary low concentration as 2×10^{-5} mg/ml, and further its vapor affects a mucosa of eye, among others, and is toxic to all respiratory organs.

[0004] Therefore, use of osmium tetroxide in an industrial scale has been troublesome, and it has been used only as an oxidizing agent for oxidizing a small amount of precious substances. Actually some technologies have been tried for the purpose of using this compound safely in an industrial scale. For instance, International Patent Publication (in Japanese) No. 505884/1992 provides a method for precipitating an osmium oxide on nitrogen-containing polymer from a solvent solution, and actually a product comprising about 1 wt % of osmium tetroxide immobilized on poly(4-vinylpyridine) (e.g. listed on a catalogue of Sigma-Aldrich) has been on the market.

[0005] However, in all of those known methods, all basic polymers containing nitrogen atoms, particularly cross-linked ones, have been used to utilize chemical binding effect between the osmium oxide and quaternary nitrogen atoms, and therefore their production has not been easy. Further, when those known compositions are used in actual reactions, the polymers immobilizing the osmium oxide are gradually decomposed under oxidizing conditions (Journal of Molecular Catalysis A: Chemical, vol. 120 (1997) p 203 right column), and therefore the problems upon handling have not yet been solved, and reuse of the compositions is still restricted.

[0006] Further, in the product disclosed in the above International Patent Publication (in Japanese) No. 505884/1992, as stated therein, the osmium oxide immobilized on polymer containing nitrogen atoms does not exist in the form of osmium tetroxide but in the form of osmium trioxide or, sometimes, oxide of a polymer or in a reduced form such as oxoanion, and thus it cannot be said that the osmium oxide is immobilized on the polymer as the stable form of osmium tetroxide and consequently the effect as an oxidizing agent of the product is apparently poor as compared with that of osmium tetroxide.

[0007] Recently, it is reported that oxidation of olefin compounds by using osmium oxide to which a chiral ligand is attached can give the corresponding chiral products ("Catalytic asymmetric synthesis, VHC Publisher, New York, 1993, P.227- 272," or "Chem. Rev., 94, 2483-2547 (1994)," etc.). But in those asymmetric oxidations, an osmium oxide itself is used without, for instance, immobilized on polymers, etc., and therefore, the recovery and reuse of the osmium oxide is usually difficult.

[0008] On the other hand, it is reported that an asymmetric oxidation is conducted using a complex of an osmium tetroxide and a polymer on which a chiral ligand is immobilized ("Eur. J. Org. Chem., 1998, 21-27" etc). However, in this method, introducing of the chiral ligand in the polymer is not so easy and further the polymer containing the chiral ligand thus obtained has to be further reacted with osmium tetroxide. Additionally, the osmium tetroxide in the complex comes off from the complex little by little during the asymmetric oxidation, and therefore reuse of the complex many times is substantially impossible.

SUMMARY OF THE INVENTION

[0009] The present inventors have extensively made study in order to solve such problems as mentioned above to realize the improvement, on the basis of which the present invention has been accomplished.

[0010] Namely, the present invention provides

an osmium oxide microencapsulated in an aromatic polyolefin (hereinafter abbreviated as MCOsO_x).

[0011] Further, the present invention provides MCOsO_x wherein a chiral ligand further coordinates to an osmium oxide (hereinafter abbreviated as MCOsO_x -chiral ligand complex).

[0012] Still further, the present invention provides a method for preparation of MCOsO_x , which comprises allowing an osmium oxide to contact with an aromatic polyolefin in an organic solvent, and precipitating MCOsO_x .

[0013] Furthermore, the present invention provides a method for preparing MCOsO_x -chiral ligand complex, which comprises allowing MCOsO_x to contact with a chiral ligand.

[0014] Still furthermore, the present invention provides a method for preparing MCOsO_x -chiral ligand complex, which comprises allowing an osmium oxide, a chiral ligand and an aromatic polyolefin to contact with one another in an organic solvent, and precipitating an osmium oxide-chiral ligand complex microencapsulated in the aromatic polyolefin (MCOsO_x -chiral ligand complex).

5 [0015] Additionally, the present invention provides an oxidizing agent comprising MCOsO_x .

[0016] Still additionally, the present invention provides an oxidizing agent comprising MCOsO_x -chiral ligand complex.

[0017] Still further additionally, the present invention provides a method for preparing a chiral diol compound, which comprises oxidizing an olefin compound with MCOsO_x -chiral ligand complex.

10 [0018] Still furthermore additionally, the present invention provides a method for preparing a chiral diol compound, which comprises reacting MCOsO_x , a chiral ligand and an olefin compound with each other.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

15 [0019] As the osmium oxide of the present invention, use is generally made of osmium tetroxide, but other osmium oxides such as osmium dioxide can be used. The osmium oxide may be commercially available one.

[0020] A part of osmium in MCOsO_x of the present invention is partly reduced by a small quantity of non-reacted unsaturated bonds usually existed in the aromatic polyolefin, and such partly reduced osmium oxide as above is also included in the osmium oxide of the present invention.

20 [0021] The aromatic polyolefin of the present invention (hereinafter sometimes abbreviated as the polymer of the present invention) includes homopolymers and copolymers which are prepared by polymerization of aromatic olefins, such as, styrene, α -substituted styrene or their ring-substituted derivatives. The substituent in the ring-substituted derivatives of styrene or α -substituted styrene may be any one which does not give bad influence on conducting the microencapsulating of osmium oxide by the method of the present invention and does not reduce the effect of the osmium oxide in MCOsO_x as an oxidizing agent or a catalyst, and includes an alkyl group such as a methyl group, an ethyl group and an isopropyl group, an alkoxy group such as a methoxy group, an ethoxy group and an isopropoxy group, etc.

25 [0022] The monomer unit other than styrene or α -substituted styrene type unit in the copolymers is not specifically limited and may be any one which does not give bad influence upon conducting the microencapsulating of osmium oxide by the method of the present invention and does not reduce the effect of the osmium oxide in MCOsO_x as an oxidizing agent or a catalyst, and includes ethylenically unsaturated carboxylic acids such as acrylic acid, methacrylic acid, maleic acid and fumaric acid, ethylenically unsaturated carboxylic acid esters such as methyl acrylate, methyl methacrylate, butyl methacrylate and dimethyl maleate, ethylenically unsaturated amide or imide compounds such as acrylamide, methacrylamide and maleimide, vinyl esters such as vinyl formate and vinyl acetate and cyano-containing ethylenically unsaturated compounds such as acrylonitrile and methacrylonitrile.

30 [0023] The copolymers of the present invention also includes those prepared by using a divalent unsaturated monomer such as butadiene and divinylbenzene together with the aromatic olefin such as styrene, α -substituted styrene and their ring-substituted derivatives, if necessary, further together with a monomer other than the styrene, α -substituted styrene and their ring-substituted derivatives. The typical examples of this type of copolymers are acrylonitrile-butadiene-styrene resin (ABS-resin) and styrenedivinylbenzene copolymer.

40 [0024] A basic nitrogen-containing monomer is not desirable as the monomer other than styrene and α -methyl styrene, but there may be used only when its amount is such one as giving no considerable influence.

[0025] In the polymer of the present invention, when the molecular weight of the aromatic polyolefin to be used is too low, a mechanical strength of the resulting MCOsO_x or MCOsO_x -chiral ligand complex becomes low, and when it is too high, the preparation of MCOsO_x or MCOsO_x -chiral ligand complex requires much work and time.

45 [0026] A weight-average molecular weight of the polymers of the present invention is generally 1,000 to 5,000,000, preferably 200,000 to 350,000, and a degree of polymerization of the polymer is 10 to 50,000, preferably 2,000 to 3,500.

[0027] As the polymers of the present invention, use may be made of those produced after a conventional method or commercially available ones.

50 [0028] The preparation of MCOsO_x of the present invention is conducted after a so-called microencapsulating technology for relatively large molecular weight substances, which has been used in medical and foodstuff fields, such as one disclosed in *Pharmaceutica Acta Helvetiae* vol.53 (1978) p 17-23 and p 33-39 as the general discussion.

[0029] Namely, the osmium oxide is allowed to contact with the aromatic polyolefin, for instance, by mixing the both, in an organic solvent until the resulting mixture becomes homogeneous and then precipitating the resultant to recover a solid part, for instance, by filtration.

55 [0030] More particularly, for instance, the polymer of the present invention as mentioned above is dissolved in a suitable organic solvent under heating with stirring. An osmium oxide such as osmium tetroxide in an amount of 0.02 to 0.4 wt part, preferably 0.1 to 0.2 wt part, relative to 1 wt part of the polymer is added to the above obtained solution, followed by stirring at 25 to 50°C until the resulting mixture becomes homogeneous. Termination of the treatment can

be confirmed by this homogeneity. The resulting homogeneous solution is ice-cooled with stirring. When precipitating out of a solid is observed, a poor solvent to the polymer used is added so as to complete the precipitating out. Recovering the precipitated product by filtration gives MCOsO_x of the present invention. It is voluntary that the obtained product is further washed and dried after a conventional manner.

[0031] The organic solvent to be used in the preparation as mentioned above is not specifically limited so long as it can dissolve the polymer of the present invention, and includes aromatic hydrocarbons such as benzene, toluene and xylene, ketones such as methyl ethyl ketone, ethers such as diethyl ether and tetrahydrofuran, esters such as ethyl acetate, halogenated hydrocarbons such as chloroform, dichloroethane and carbon tetrachloride, saturated cyclic hydrocarbons such as cyclohexane, etc. Preferable solvent is variable because it depends upon the kind of the polymer to be used, and when polystyrene is used, for instance, cyclohexane, dichloroethane, etc. is preferable because it has a suitable solubility to polystyrene. When ABS-resin is used, for instance, tetrahydrofuran is preferable because it has a suitable solubility to ABS-resin.

[0032] The poor solvent to the polymer to be used in the preparation as mentioned above somewhat depends upon the kind of the polymer, and includes lower alcohols such as methanol and ethanol, aliphatic hydrocarbons such as n-hexane and petroleum ether, etc., among which methanol is preferable from industrial point of view.

[0033] MCOsO_x -chiral ligand complex of the present invention is prepared, for example, by a method mentioned below.

[0034] Namely, for instance, MCOsO_x and a chiral ligand in an amount of 0.001 to 10 mol%, preferably 0.1 to 1 mol%, relative to 1 mol% of the osmium oxide in MCOsO_x are added to a suitable solvent, followed by stirring at 0 to 50°C, preferably 15 to 40 °C for a few minutes to a few ten minutes. Recovering the precipitation by filtration gives MCOsO_x -chiral ligand complex of the present invention. It is voluntary that the obtained product is further washed and dried after a conventional manner.

[0035] The solvent to be used in the preparation method mentioned above is not specifically limited so long as it cannot dissolve MCOsO_x of the present invention under the condition for conducting an object reaction and give any bad influence on an object reaction, and includes water, acetonitrile, dimethylformamide, dimethyl sulfoxide, ketones such as acetone and methyl ethyl ketone, lower alcohols such as methanol, ethanol and isopropanol, ethers such as diethyl ether, 1,4-dioxane and tetrahydrofuran, esters such as ethyl acetate, hydrocarbons such as benzene, toluene, xylene and cyclohexane, halogenated hydrocarbons such as chloroform, dichloroethane and carbon tetrachloride, etc.

[0036] These solvents may be used alone or in a suitable combination of two or more thereof. In case of the combination of two or more thereof, there is exemplified by a mixed solvent of water, acetonitrile and acetone as a preferable combination of these solvents.

[0037] MCOsO_x -chiral ligand complex of the present invention is also prepared by allowing an osmium oxide, a chiral ligand and the polymer of the present invention to contact with one motion in a suitable organic solvent after the above-mentioned manner for the production of MCOsO_x .

[0038] More particularly, for instance, the polymer of the present invention as mentioned above is dissolved in a suitable organic solvent under heating with stirring. An osmium oxide such as osmium tetroxide in an amount of 0.02 to 0.4 wt part, preferably 0.1 to 0.2 wt part, relative to 1 wt part of the polymer and a chiral ligand in an amount of 0.001 to 10 mol%, preferably 0.1 to 1 mol%, relative to 1 mol% of the osmium oxide are added to the above obtained solution, followed by stirring at 25 to 50°C until the resultant becomes homogeneous. Termination of the treatment on can be confirmed by this homogeneity. The resulting homogeneous solution is ice-cooled with stirring. When precipitating out of a solid is observed, a poor solvent to the polymer used is added so as to complete the precipitating out. Recovering the precipitated product by filtration gives MCOsO_x -chiral ligand complex of the present invention. It is voluntary that the obtained product is further washed and dried after a conventional manner.

[0039] The chiral ligand used in the present invention includes compounds having the following properties;

- a) having optical activity
- b) including generally one or more, preferably two or more ligands which have a lone pair, and
- c) having a bulky structure.

[0040] The chiral ligands having the above properties are particularly preferable in a case of using them together with MCOsO_x in asymmetric oxidization reaction.



[0041] The ligand having a lone pair mentioned above is one derived from oxidizing accelerator, including tertiary amine compounds such as pyridine compounds (i.e. pyridine, a substituted pyridine derivative, etc.), quinuclidine compounds (i.e. quinuclidine, a substituted quinuclidine derivative, etc.), an N-substituted piperidine derivative and phthalazine.


[0042] The bulky structure mentioned above is, for instance, a cyclic structure, which may be any of a monocyclic structure or a polycyclic structure, and includes one derived from aliphatic cyclic hydrocarbon rings such as a cyclopentane ring and a cyclohexane ring, aromatic rings such as a benzene ring, a naphthalene ring and an anthracene ring,

aliphatic heterocyclic rings such as a pyrrolidine ring, a piperidine ring and a quinuclidine ring, aromatic heterocyclic rings such as a pyridine ring, a pyrazine ring, a pyrimidine ring, a pyridazine ring, an indole ring, an isoquinoline ring, a quinoline ring, a phthalazine ring and a pyrazino[2,3-d]pyridazine ring, and their ring-substituted derivatives, whose substituent has no bad influence upon the object reaction.


[0043] The substituent includes alkyl groups of 1 to 6 carbon atoms such as a methyl group, an ethyl group, an n-propyl group, an isopropyl group, a cyclopropyl group, an n-butyl group, an isobutyl group, a sec-butyl group, a tert-butyl group, an n-pentyl group, an isopentyl group, a neopentyl group, a tert-pentyl group, a 3,3-dimethylbutyl group, a 1,1-dimethylbutyl group, a 1-methylpentyl group, a cyclopentyl group, an n-hexyl group, an isohexyl group and a cyclohexyl group, alkoxy groups of 1 to 6 carbon atoms such as a methoxy group, an ethoxy group, an n-propoxy group, an isopropoxy group, a cyclopropoxy group, an n-butoxy group, an isobutoxy group, a sec-butoxy group, a tert-pentyloxy group, a 3,3-dimethylbutoxy group, a 1,1-dimethylbutoxy group, a 1-methylpentyloxy group, a cyclopentyloxy group, an n-hexyloxy group, an isohexyloxy group and a cyclohexyloxy group, halogen atoms such as a chlorine atom, a bromine atom, a fluorine atom and an iodine atom, a thiol group, an amino group and a phenoxy group which may have a substituent such as alkyl groups of 1 to 6 carbon atoms.

[0044] Among the chiral ligands having the above properties, more preferable examples include ones which can catalyze the general asymmetric oxidation reaction using an osmium oxide such as osmium tetroxide. The specific examples of the ligands are as below, which may have substituents having no bad influence upon the reaction.





















R = H (DHQD)








R = H (DHQ)






a : R=acetyl
b : R=p-chlorobenzoyl




5




10

15



20


25



30

35


40



45

50

55



[0045] The organic solvent to be used in the preparation method mentioned above is not specifically limited so long as it can dissolve the polymer of the present invention, and includes aromatic hydrocarbons such as benzene, toluene and xylene, ketones such as methyl ethyl ketone, ethers such as diethyl ether, 1,4-dioxane and tetrahydrofuran, esters such as ethyl acetate, halogenated hydrocarbons such as chloroform, dichloroethane and carbon tetrachloride, saturated cyclic hydrocarbons such as cyclohexane, etc. Preferable solvent is variable because it depends upon the kind of the polymer to be used, and when polystyrene is used, for instance, cyclohexane, dichloroethane, etc. are preferable because they have a suitable solubility to polystyrene. When ABS-resin is used, for instance, tetrahydrofuran is preferable, because it has a suitable solubility to ABS-resin.

[0046] These solvents may be used alone or in a suitable combination of two or more thereof.

[0047] The poor solvent to the polymer to be used in the preparation as mentioned above somewhat depends upon the kind of the polymer, and includes lower alcohols such as methanol and ethanol, aliphatic hydrocarbons such as n-hexane and petroleum ether, etc., among which methanol is preferable from industrial point of view.

[0048] In thus obtained MCOsO_x or MCOsO_x -chiral ligand complex of the present invention, the osmium oxide is contained, presumably in microencapsulated state in the polymer of the present invention, and is considered to be maintained in the microcapsule formed by the polymer of the present invention by electronic interaction between the aromatic ring of the polymer and a vacant orbit of the osmium.

[0049] The resulting product comprises fine particles having an average particle size of 100 to 200 μm .

[0050] The characteristics of the product are as follows;

1. an osmium oxide is in microencapsulated state and thus can safely be handled,
2. no smell peculiar to an osmium oxide is perceived any longer even when it is kept standing under usual atmosphere,
3. the product shows such high storage stability that it can maintain its activity even after 12 months storage, while the activity of conventional products is reduced after 6 months storage even under tightly sealed conditions (Synthesis, p46, 1989 right column), and
4. after the product is used as an oxidizing agent, it can be recovered quantitatively and thus recovered product can be reused repeatedly. For instance, even after reusing the product ten times or more, almost no reduction of the catalytic activity of the product is observed.

[0051] These characteristics suggest that the osmium oxide is coated or covered by the polymer as a matrix, and that whole structure does not collapse during storage or even after using as an oxidizing agent, while its activity, for instance, as an oxidizing agent, can be maintained, and further these characteristics support such presumption on a concrete structure of the product that each of fine particles of the osmium oxide is microencapsulated or included in the polymer as a matrix but the microencapsulation or inclusion in this case is not complete so that the microencapsulated or included particles have fine holes or pores which directly connect to atmosphere (see Pharmaceutica Acta Helveticae vol.53 (1978) p 17-23 and p 33-39). In other words, it is presumed that the osmium oxide microencapsulated or included in the polymer as a matrix is not completely shielded to atmosphere.

[0052] In MCOsO_x or MCOsO_x -chiral ligand complex of the present invention, it is possible to contain an osmium oxide in an amount of 10 % or more, at maximum about 20 %, while conventional products contain it only in about 1 % at most, and also in this respect, the present composition is remarkably excellent as compared with conventional products.

[0053] MCOsO_x or MCOsO_x -chiral ligand complex of the present invention can be formulated into various forms depending upon the kind of the poor solvent used and conditions for adding the osmium oxide to the polymer, and even when it is formulated into a bulk form, the product can be put into practical use after pulverizing upon necessity.

[0054] MCOsO_x or MCOsO_x -chiral ligand complex of the present invention can be used as an oxidizing agent in oxidizing reactions of organic compounds, quite similarly to osmium tetroxide itself. The use for this purpose may follow

conventional ones in oxidizing reactions of organic compounds by osmium tetroxide, and the total amount of MCOsO_x or MCOsO_x -chiral ligand complex to be used can be determined on the basis of the osmium oxide content in MCOsO_x or MCOsO_x -chiral ligand complex so that an osmium oxide can exist in the reaction system in an amount necessary to the reaction.

[0055] When MCOsO_x or MCOsO_x -chiral ligand complex of the present invention is used as an oxidizing agent, other conventional oxidizing agent can be co-used therewith. Other oxidizing agent co-usable may be any one which has been used in oxidizing reactions of organic compounds with the use of osmium tetroxide, and includes hydrogen peroxide, potassium ferricyanide, potassium periodate, sodium periodate, organic peroxides such as t-butyl hydroperoxide, N-oxide compound such as 4-methylmorpholine N-oxide and trimethylamine N-oxide.

[0056] In addition, the above-mentioned oxidation reaction using MCOsO_x and a chiral ligand, or using MCOsO_x -chiral ligand complex of the present invention includes asymmetric oxidation reaction. In these oxidation reactions, stereoselective oxidation of olefin compounds having a chiral carbon atom, diastereoselective oxidation of olefin compounds having a chiral protective groups, and enantiomeric asymmetric oxidation are included and MCOsO_x of the present invention with a chiral ligand, or MCOsO_x -chiral ligand complex of the present invention is able to use in all of these asymmetric oxidations.

[0057] For instance, a chiral diol compound is obtained at high optical yield by subjecting an olefin compound to an asymmetric oxidation reaction using MCOsO_x and a chiral ligand, or using MCOsO_x -chiral ligand complex.

[0058] Preparation method for a chiral diol compound of the present invention can be conducted by a method mentioned below.

[0059] Namely, for instance, MCOsO_x and a chiral ligand in an amount of 0.001 to 10 mol%, preferably 0.1 to 1 mol%, relative to 1 mol% of the osmium oxide in MCOsO_x are added to a suitable solvent, and an olefin compound in an amount of 1 to 100,000 mol%, preferably 1 to 100 mol%, relative to 1 mol% of the osmium oxide in MCOsO_x is dropwisely added to the resulting solution, if necessary, in the presence of other suitable oxidizing agent, generally at 0 to 80°C, preferably at 15 to 40°C, generally for 5 to 50 hours, preferably for 20 to 30 hours, whereby the object asymmetric oxidation reaction takes place. After the reaction, MCOsO_x -chiral ligand complex is removed by filtration and the filtrate is subjected to a conventional suitable after-treatment, whereby the objective chiral diol compound can easily be obtained at high optical yield.

[0060] Also, such an asymmetric oxidation reaction can be conducted by reacting an olefin compound with MCOsO_x -chiral ligand complex, which is previously prepared.

[0061] Namely, the chiral diol compound can be obtained by either of the above two methods.

[0062] However, the former method in which a preparation of MCOsO_x -chiral ligand complex and an asymmetric oxidation of an olefin are conducted in so-called one-pot reaction is preferable, for the reason that it needs less amount of a chiral ligand for the asymmetric oxidation reaction than the latter.

[0063] The olefin compound to be used in the method of preparing a chiral diol compound mentioned above is not specifically limited so long as it has generally one or more, preferably one or two polymerizable double bond in its molecule, and includes an aliphatic olefin, an aromatic olefin, etc.

[0064] The solvent to be used in the method mentioned above is not specifically limited so long as it does not dissolve MCOsO_x or MCOsO_x -chiral ligand complex of the present invention under the condition for conducting an object reaction and give any bad influence on an object reaction, and according to properties of MCOsO_x or MCOsO_x -chiral ligand complex and an olefin compound to be used, use is made of water, acetonitrile, dimethylformamide, dimethyl sulfoxide, ketones such as acetone and methyl ethyl ketone, lower alcohols such as methanol, ethanol and isopropanol, ethers such as diethyl ether, 1,4-dioxane and tetrahydrofuran, esters such as ethyl acetate, hydrocarbons such as benzene, toluene, xylene and cyclohexane, halogenated hydrocarbons such as chloroform, dichloroethane and carbon tetrachloride, etc.

[0065] These solvents may be used alone or in a suitable combination of two or more thereof. In case of the combination of two or more thereof, there is exemplified by a mixed solvent of water, acetonitrile and acetone as a preferable combination of these solvent.

[0066] MCOsO_x -chiral ligand complex used in the above mentioned reaction can be recovered quantitatively and thus recovered MCOsO_x -chiral ligand complex can be reused repeatedly for an asymmetric oxidation reaction.

[0067] In order to increase an optical yield of a chiral diol compound, it is desired to co-use an additional chiral ligand in the case of reusing MCOsO_x -chiral ligand complex three times or more.

[0068] Further, in order to increase oxidation activity of MCOsO_x , it is desired to co-use other oxidizing agent mentioned above.

[0069] In the following, the present invention is further explained referring to Examples, but the present invention is not limited thereto by any means.

EXAMPLE**Example 1. Preparation of MCOsO_x (Using polystyrene)**

[0070] Five grams of polystyrene (molecular weight 280,000) was dissolved in 100 ml of cyclohexane with stirring at 50 to 60°C, and then 1 g of osmium tetroxide was added to the mixture, followed by stirring for about 1 hour until the mixture becomes homogeneous. The resulting mixture was cooled to 25°C and then further ice-cooled. When polystyrene started to solidify, about 150 ml of methanol was added to the mixture. After standing for 8 hours, the precipitates were recovered by filtration, washed with methanol and dried under vacuum to give 5.7 g of MCOsO_x microencapsulating 700 mg of osmium oxide (hereinafter abbreviated as PS-MCOsO_x).

Example 2. Preparation of MCOsO_x (in case of Using ABS-resin)

[0071] Ten grams of ABS-resin was added in 200 ml of tetrahydrofuran (THF) and the mixture was heated at 70 to 80°C with stirring. And then 2 g of osmium tetroxide was added to the ABS-resin of THF solution, followed by stirring for about 1 hour until the mixture becomes homogeneous. The resulting mixture was cooled to 25°C and then further ice-cooled. When the resin started to solidify, about 300 ml of n-hexane was added to the mixture. After standing for 8 hours, the precipitates were recovered by filtration, washed with methanol and dried under vacuum to give 11.9g of MCOsO_x microencapsulating 1.9 g of osmium oxide (hereinafter abbreviated as ABS-MCOsO_x).

Example 3. Preparation of ABS-MCOsO_x having a chiral ligand

[0072] The mixture of ABS- MCOsO_x(0.5 mmol as OsO₄), obtained by example 2, and hydroquinidine 1,4-phthalazinediyl diether ((DHQD)₂PHAL) as a chiral ligand (1 mmol) were added to a mixture of water-acetonitrile-acetone (1:1:1, by vol.) (35ml) with stirring by 10 minutes, and the precipitate was isolated by filtration, washed with methanol and dried to give a complex of ABS-MCOsO_x and (DHQD)₂PHAL (hereinafter abbreviated as ABS-MCOsO_x-(DHQD)₂PHAL).

Example 4. An oxidizing reaction by PS-MCOsO_x

[0073] 2.5 Millimole of 3β-cholestanol was dissolved in 50 ml of diethyl ether, and MCOsO_x containing osmium tetroxide in an amount equivalent to 2.5 mmol was added thereto, followed by stirring at 25°C for 30 hours to cause a reaction to take place. MCOsO_x was removed from the reaction solution, and a crude keto compound was recovered from the filtrate and purified by silica gel column chromatography (eluent: benzene) to give 3-cholestanon at a yield of 90 %.

Example 5. An oxidizing reaction by PS-MCOsO_x together with N-oxide

[0074] Fifty mmol of cyclohexene, 5 mole % of PS-MCOsO_x and 1.3 equivalent of N-methylmorpholine N-oxide (NMO) were stirring in mixed solvents comprising 15 ml of water, 15 ml of acetone and 15 ml of acetonitrile under argon streams at 25°C for 24 hours to allow a reaction to take place. Then about 150 ml of methanol was added to the resultant to terminate the reaction and PS-MCOsO_x was removed by filtration. The filtrate was concentrated under reduced pressure and the resulting crude product was purified by silica gel column chromatography to give 1,2-cyclohexane diol at a yield of 84 %.

[0075] Similarly to the above, analogous reactions were further conducted using ten kinds of olefin compound as substrate to give the result as shown in Table 1. In Table 1, a case of using cyclohexene as an olefin compound was also shown. The PS-MCOsO_x recovered was able to reuse after washing with methanol.

Table 1

Olefin	Reaction temperature	Reaction time	Yield (%)
Cyclohexene	25°C	24 hrs.	84
Cyclooctene	25°C	38 hrs.	81
1-Decene	25°C	24 hrs.	68
3-Hexene	25°C	48 hrs.	74
1-Hexene	25°C	24 hrs.	89
vinylcyclohexane	25°C	24 hrs.	83
methylenecyclohexane	25°C	24 hrs.	84

Table 1 (continued)


Olefin	Reaction temperature	Reaction time	Yield (%)
2-methyl-1-pentene	25°C	24 hrs.	78
1-methylcyclohexene	25°C	24 hrs.	76
3-methyl-2-butene	25°C	24 hrs.	63
2-methyl-2-heptene	60°C	24 hrs.	83

Example 6. Recovery and reuse of PS-MCOsO_x

[0076] The process in the above Example 5 was repeatedly conducted using PS-MCOsO_x recovered and change in the oxidizing effect as an oxidizing agent was studied. Consequently, such a good result as below was obtained. Namely, the yield of 1,2-cyclohexane diol after the 8th run was 85 %, while those before the 8th run were 83 to 85% , and the recovery rate of PS-MCOsO_x was almost quantitative.

Example 7. Asymmetric oxidation with ABS-MCOsO_x having a chiral ligand

[0077] NMO (1.43 mmol) was added to a slurry of ABS-MCOsO_x (0.5mmol as OsO₄) and (DHQD)₂PHAL (1mmol) in water-acetonitrile-acetone (1:1:1, vol.) (3.5 ml), and then trans-β-methylstyrene (1.1 mmol) was dropped to the slurry at 25°C for 24 hours. The ABS-MCOsO_x-(DHQD)₂PHAL was filtered off and washed with MeOH. A mixture of the filtrate and the washing solvent was concentrated under reduced pressure, and the resulting residue was purified by silica gel column chromatography to obtain a diol compound represented by formula [1] mentioned below at a yield of 95%. The optical yield of the diol compound was 85%ee. Since osmium was not detected in the filtrate, osmium tetroxide did not leak out from the ABS-MCOsO_x-(DHQD)₂PHAL.



Example 8. Asymmetric oxidation with PS-MCOsO_x having a chiral ligand

[0078] Trans-β-methylstyrene was oxidized with PS-MCOsO_x (0.5 mmol as OsO₄) instead of ABS-MCOsO_x after the asymmetric oxidation of example 7 to give a diol compound at a yield of 80%. The optical yield of the diol compound was 56%ee.

Example 9. Recovery and reuse of ABS-MCOsO_x having a chiral ligand in asymmetric oxidation

[0079] The process in the Example 7 was repeatedly conducted using recovered ABS-MCOsO_x-(DHQD)₂PHAL for the study of changing in the oxidizing ability of ABS-MCOsO_x-(DHQD)₂PHAL as an oxidizing agent. Consequently, the object diol compound was obtained at a yield of 99%, and the optical yield of the diol compound was 86%ee.

[0080] As mentioned above, the osmium oxide microencapsulated in the aromatic polyolefin of the present invention can more easily be prepared as compared with osmium oxides immobilized on a basic nitrogen-containing polymer, and though the product contains high concentration of osmium oxide, it can safely be handled under normal conditions, and further it is excellent in its reactivity. Therefore, it can be utilized in oxidizing reactions of organic compounds quite similarly to osmium tetroxide, and it can quantitatively be recovered and can be reused. Further in case of oxidizing reaction of an olefin compound using it together with a chiral ligand, a chiral diol compound can be obtained at high optical yield. Because of those characteristics, the composition of the present invention is such a valuable one as being able to be utilized easily and at high efficacy in an industrial scale.

Claims

1. An osmium oxide microencapsulated in an aromatic polyolefin.

2. The osmium oxide according to claim 1, wherein the osmium oxide is osmium tetroxide.
3. The osmium oxide according to claim 1, wherein the aromatic polyolefin is a homopolymer or a copolymer of styrene, α -substituted styrene or their ring-substituted derivative.
- 5 4. The osmium oxide according to claim 1, wherein the aromatic polyolefin is polystyrene or acrylonitrile-butadiene-styrene resin.
- 10 5. An osmium oxide according to claim 1, wherein a chiral ligand further coordinates to the osmium oxide.
6. A method for preparation of an osmium oxide claimed in claim 1, which comprises allowing the osmium oxide to contact with an aromatic polyolefin in an organic solvent, and precipitating the osmium oxide microencapsulated in the aromatic polyolefin.
- 15 7. The method according to claim 6, wherein the osmium oxide is mixed with an aromatic polyolefin in an organic solvent until the resulting mixture becomes homogeneous and precipitating the resultant to recover a solid part.
8. The method according to claim 6, wherein the osmium oxide is osmium tetroxide.
- 20 9. The method according to claim 6, wherein the aromatic polyolefin is a homopolymer or a copolymer of styrene, α -substituted styrene or their ring-substituted derivative.
10. The method according to claim 6, wherein the aromatic polyolefin is polystyrene or acrylonitrile-butadiene-styrene resin.
- 25 11. A method for preparing an osmium oxide claimed in claim 5, which comprises allowing the osmium oxide claimed in claim 1 to contact with a chiral ligand.
- 30 12. A method for preparing an osmium oxide claimed in claim 5, which comprises allowing an osmium oxide, a chiral ligand and an aromatic polyolefin to contact with one another in an organic solvent, and precipitating the osmium oxide-chiral ligand complex microencapsulated in the aromatic polyolefin.
13. An oxidizing agent comprising an osmium oxide claimed in claim 1.
- 35 14. The oxidizing agent according to claim 13, wherein the osmium oxide is osmium tetroxide.
15. The oxidizing agent comprising an osmium oxide claimed in claim 5.
- 40 16. A method for preparing a chiral diol compound, which comprises oxidizing an olefin compound with an osmium oxide claimed in claim 5.
17. A method for preparing a chiral diol compound, which comprises reacting an osmium oxide claimed in claim 1, a chiral ligand and an olefin compound with each other.
- 45 18. The method according to claim 16 or 17, wherein the olefin compound is an aliphatic olefin or an aromatic olefin.

Patentansprüche

- 50 1. Osmiumoxid, das in einem aromatischen Polyolefin mikroverkapselt ist.
2. Osmiumoxid gemäß Anspruch 1, wobei das Osmiumoxid Osmiumtetroxid ist.
3. Osmiumoxid gemäß Anspruch 1, wobei das aromatische Polyolefin ein Homopolymer oder ein Copolymer von Styrol, α -substituiertem Styrol oder ihrem ringsubstituierten Derivat ist.
- 55 4. Osmiumoxid gemäß Anspruch 1, wobei das aromatische Polyolefin Polystyrol oder Acrylnitril-Butadien-Styrol-Harz ist.

5. Osmiumoxid gemäß Anspruch 1, wobei das Osmiumoxid weiter mit einem chiralen Liganden koordiniert ist.
6. Verfahren zur Herstellung eines in Beispiel 1 beanspruchten Osmiumoxids, das das Erlaubenlassen dem Osmiumoxid, mit einem aromatischen Polyolefin in einem organischen Lösungsmittel in Berührung zu gelangen und Füllen des in dem aromatischen Polyolefin mikroverkapselten Osmiumoxids umfaßt.
7. Verfahren gemäß Anspruch 6, wobei das Osmiumoxid mit einem aromatischen Polyolefin in einem organischen Lösungsmittel gemischt wird, bis das sich daraus ergebende Gemisch homogen wird, und das sich daraus Ergebende unter Isolieren eines festen Anteils ausgefällt wird.
8. Verfahren gemäß Anspruch 6, wobei das Osmiumoxid Osmiumtetroxid ist.
9. Verfahren gemäß Anspruch 6, wobei das aromatische Polyolefin ein Homopolymer oder ein Copolymer von Styrol, α -substituiertem Styrol oder ihrem ringsubstituierten Derivat ist.
10. Verfahren gemäß Anspruch 6, wobei das aromatische Polyolefin Polystyrol oder Acrylnitril-Butadien-Styrol-Harz ist.
11. Verfahren zum Herstellen eines in Anspruch 5 beanspruchten Osmiumoxids, das das Erlaubenlassen dem in Anspruch 1 beanspruchten Osmiumoxid, mit einem chiralen Liganden in Berührung zu gelangen, umfaßt.
12. Verfahren eines in Anspruch 5 beanspruchten Osmiumoxids, das das Erlaubenlassen einem Osmiumoxid, einem chiralen Liganden und einem aromatischen Polyolefin in einem organischen Lösungsmittel miteinander in Berührung zu gelangen und Füllen des in dem aromatischen Polyolefin mikroverkapselten Komplexes aus Osmiumoxid und chiralem Liganden umfaßt.
13. Oxidationsmittel umfassend ein in Anspruch 1 beanspruchtes Osmiumoxid.
14. Oxidationsmittel gemäß Anspruch 13, wobei das Osmiumoxid Osmiumtetroxid ist.
15. Oxidationsmittel umfassend ein in Anspruch 5 beanspruchtes Osmiumoxid.
16. Verfahren zum Herstellen einer chiralen Diolverbindung, das das Oxidieren einer Olefinverbindung mit einem in Anspruch 5 beanspruchten Osmiumoxid umfaßt.
17. Verfahren zum Herstellen einer chiralen Diolverbindung, das das Umsetzen eines in Anspruch 1 beanspruchten Osmiumoxids, eines chiralen Liganden und einer Olefinverbindung miteinander umfaßt.
18. Verfahren gemäß Anspruch 16 oder 17, wobei die Olefinverbindung ein aliphatisches Olefin oder ein aromatisches Olefin ist.

Revendications

1. Oxyde d'osmium microencapsulé dans une polyoléfine aromatique.
2. Oxyde d'osmium conforme à la revendication 1, qui est du tétraoxyde d'osmium.
3. Oxyde d'osmium conforme à la revendication 1, dans lequel la polyoléfine aromatique est un homopolymère ou un copolymère de styrène, ou d'un dérivé du styrène portant un substituant en position α et/ou sur le cycle.
4. Oxyde d'osmium conforme à la revendication 1, dans lequel la polyoléfine aromatique est un polystyrène ou une résine acrylonitrilebutadiène-styrène.
5. Oxyde d'osmium conforme à la revendication 1, dans lequel un ligand chiral est en outre coordonné avec l'oxyde d'osmium.
6. Procédé de préparation d'un oxyde d'osmium conforme à la revendication 1, qui comporte le fait de mettre de

l'oxyde d'osmium en contact avec une polyoléfine aromatique dans un solvant organique, et le fait de faire précipiter l'oxyde d'osmium microencapsulé dans la polyoléfine aromatique.

- 5 7. Procédé conforme à la revendication 6, dans lequel on mélange l'oxyde d'osmium avec une polyoléfine aromatique, dans un solvant organique, jusqu'à obtenir un mélange homogène, et l'on soumet le mélange résultant à une opération de précipitation, pour récupérer une fraction solide.
8. Procédé conforme à la revendication 6, dans lequel l'oxyde d'osmium est du tétraoxyde d'osmium.
- 10 9. Procédé conforme à la revendication 6, dans lequel la polyoléfine aromatique est un homopolymère ou un copolymère de styrène, ou d'un dérivé du styrène portant un substituant en position alpha et/ou sur le cycle.
10. Procédé conforme à la revendication 6, dans lequel la polyoléfine aromatique est un polystyrène ou une résine acrylonitrilebutadiène-styrène.
- 15 11. Procédé de préparation d'un oxyde d'osmium conforme à la revendication 5, qui comporte le fait de mettre un oxyde d'osmium conforme à la revendication 1 en contact avec un ligand chiral.
- 20 12. Procédé de préparation d'un oxyde d'osmium conforme à la revendication 5, qui comporte le fait de mettre de l'oxyde d'osmium, un ligand chiral et une polyoléfine aromatique en contact les uns avec les autres dans un solvant organique, et le fait de faire précipiter le complexe d'oxyde d'osmium et de ligand chiral, microencapsulé dans la polyoléfine aromatique.
- 25 13. Agent oxydant contenant un oxyde d'osmium conforme à la revendication 1.
14. Agent oxydant conforme à la revendication 13, dans lequel l'oxyde d'osmium est du tétraoxyde d'osmium.
15. Agent oxydant contenant un oxyde d'osmium conforme à la revendication 5.
- 30 16. Procédé de préparation d'un diol chiral, qui comporte le fait d'oxyder une oléfine au moyen d'un oxyde d'osmium conforme à la revendication 5.
17. Procédé de préparation d'un diol chiral, qui comporte le fait de faire réagir les uns sur les autres un oxyde d'osmium conforme à la revendication 1, un ligand chiral et une oléfine.
- 35 18. Procédé conforme à la revendication 16 ou 17, dans lequel l'oléfine est une oléfine aliphatique ou une oléfine aromatique.

40

45

50

55